

安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号 日月科技园

电话: 86-552-3827158 传真: 86-552-3822922

TDS of IOTA 273 Vinyl silicone oil

Structural Formula

Description

- 1. This product is the end vinyl polydimethylsiloxane. It's an excellent and lively intermediate material
- 2. The product has the methyl silicone oil's common performance(such as : smoothness, limpness, bright, temperature and durability etc.
- 3.Two ends of vinyl have very strong reactivity, can have addition reaction with hydrogen silicone when under the action of catalyst .also can participate in a variety of other reactions.
- 2. Has better intermiscibility with organic material compare to methyl silicone oil, easier compatibility with other organic materials.
- 3. For containing lively double bond, easy to have reaction with organic material such as polyurethane, acrylic acid etc.

CAS: 68083-19-2

Typical Properties

Viscosity	Molecular weight	Vinyl content (%)	Density
(25°C,MPas)			
0.7	186	29	0.81
2-3	500	10-12	0.92
4-6	770	7-9	0.93
10	1000	5.4	0.95
20	2000	2.7	0.95

Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.personalcaresilicone.com



安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

安徽省蚌埠市高新区兴中路 985 号 日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

100	6000	0.8-1.2	0.97
200	9400	0.4-0.6	0.97
500	17200	0.37-0.43	0.97
1000	28000	0.18-0.26	0.97
3500	43000	0.12-0.15	0.97
5000	49500	0.10-0.13	0.97
10000	62700	0.08-0.12	0.97
20000	72000	0.06-0.09	0.98
65000	117000	0.04-0.06	0.98
165000	155000	0.03-0.04	0.98

Application:

- 1. Use as high temperature vulcanizing silicone rubber (HTV) for the production of basic raw material, to enhance the hardness and strength of silicone rubber.
- 2. For the production of liquid silicone rubber, it's the main material of injection molding silicone rubber.
- 3. This product reaction with organic material such as polyurethane, acrylic acid etc., Can produce new material that have preferable performance (weathering resistance, ageing resistance, uvioresistant, reinforcing and toughening etc.) wide usages in the plastic, resin, paint, and coatings modified.

Usage And Dosage

When used as additive or modified the quantity of 10%-20%, when used as base gule the quantity of 50%-100%

Package and Transportation

1. This product should be stored airtight at room temperature in dry shade, not near the



安徽艾约塔硅油有限公司

IOTA CORPORATION LTD.

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

安徽省蚌埠市高新区兴中路 985 号

日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

fire source, avoid sun exposure, avoid mixing of impurities (especially catalysts, acid substances);

- 2. With a 200 kg drum or 50 kg clean polyethylene plastic barrel packaging
- 3. Non-dangerous goods storage and transportation.

Notices

This material have chemistry's lively, should not to mixed with impurities(especially the catalyst), when in use or compatibility of medicines, should be notice if have chemical reaction, prevent degeneration.

IOTA CORPORATION LTD.

Add: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

TeL: 0086-552-7183958 Fax: 0086-552-3822922

Mobile/What's app/Wechat: 0086-18055289988

Skype: arielyang1988

QQ: 2302519534

Email: info@personalcaresilicone.com

Website: www.personalcaresilicone.com